

纺织工业(苏州)检测中心

Textile Industry Testing Center-Suzhou

苏州中科纺织技术服务有限公司

Suzhou Zhongke Textile Technology Service Co., Ltd.



地址:中国江苏省苏州市盛泽镇西三环路999号色坯商城北附楼 North Attached Building, No.999, West Second Rd. Shengze Town, Suzhou City, Jiangsu Province.

Http://www.fcl-sz.org.cn Tel:+86 512 63081315 Fax:+86 512 63515926

TESTING REPORT	Report No.	FCW0174527
	Date	2012-01-11
ORIGINAL	Page	Page 1 of 3

Applicant Name

:Wujiang Sarytex co.,LTD.

Contact Person

:Cai Zhongyi

The following sample(s) was/were submitted and identified on behalf of the client as :

A Sample Description

:A black woven fabric (385.735)

Style No

:SA0014

Style Name

:380T nylon taffta

B Sample Description

:A white woven fabric (385.304)

Style No

:SA0013

Style Name

:380T nylon taffta

C Sample Description

:A white woven fabric (378.304)

Style No

:SA0013

Style Name

:350T nylon taffta

- Selected test(s) as requested by applicant.
- The original sample is sticked on the last paper.

Sample Receiving date

:2012-01-10

Tests Started date

:2012-01-10

Test Result(s): For further details, please refer to the following page(s).

Signed for and on behalf of

Textile industry testing center-Suzhou



Pronounce(声明):

The results shown in this report refer only to sample(s) tested unless otherwise stated. (除非有其他说明,测试结果只对来样负责。) The test report cannot be reproduced, except in full.(本报告只能全部复制,不得部分复制。)





纺织工业(苏州)检测中心

Textile Industry Testing Center-Suzhou





地址:中国江苏省苏州市盛泽镇西二环路999号色坯商城北附楼 North Attached Building, No.999, West Second Rd. Shengze Town, Suzhou City, Jiangsu Province.

Http://www.fcl-sz.org.cn Tel:+86 512 63081315 Fax:+86 512 63515926

TESTING REPORT	Report No.	FCW0174527
	Date	2012-01-11
ORIGINAL	Page	Page 2 of 3

--- Test Result ---

1. Dimensional Stability to Washing (ISO 3759:2011,ISO 5077:2007,ISO 6330:2000,Washing Program No.6A)

Machine Wash at 40°C with "ECE" detergent, tumble drying.

	A	В	С
After 1st cycle washing			
Lengthwise	-2.0 %	-2.0 %	-2.3 %
Widthwise	-2.5 %	-0.8 %	-1.2 %

Remarks: (+) means extension and (-) means shrinkage.

2. Penetration Resistance to Feather and Down(GB/T 12705.2:2009,tumble test)

The down for test is grey duck down of 70%.

Number of downs

C 3

Remarks: > 15 downs denotes the sample has poor down-proof properties;

6-15 downs denotes the sample has down-proof properties; < 5 downs denotes the sample has good down-proof properties.

End of Test Result ---





纺织工业(苏州)检测中心 Textile Industry Testing Center-Suzhou

苏州中科纺织技术服务有限公司







2011100973C

地址:中国江苏省苏州市盛泽镇西二环路999号色坯商城北附楼 North Attached Building, No.999, West Second Rd. Shengze Town, Suzhou City, Jiangsu Province.

Http://www.fcl-sz.org.cn Tel:+86 512 63081315 Fax:+86 512 63515926

TESTING REPORT	Report No.	FCW0174527	
	Date	2012-01-11	
ORIGINAL	Page	Page 3 of 3	

Original sample



В





C



Pronounce(声明):